

Broadband Power GaAs MESFET Chips

- ❑ **P_{1dB} Power:**
 - CF003-01: +22 dBm
 - CF005-01: +25 dBm
 - CF010-01: +28 dBm
- ❑ **High Gain (@ 12 GHz):**
 - CF003-01: 9.0 dB
 - CF005-01: 8.5 dB
 - CF010-01: 8.0 dB
- ❑ **Broadband: Usable to 18 GHz**
- ❑ **Wafer Qualification Procedure**
- ❑ **Customer Wafer Selection Available**

Celeritek Broadband Power Chips

Celeritek Medium Power Chips are GaAs MESFETs which include the CF003-01, CF005-01 and CF010-01 models. They are 600 μm , 1200 μm and 2400 μm gate width, respectively. All have sub-half-micron gate lengths, Celeritek's proprietary Silicon Nitride passivation, and are fabricated on ion implanted wafers.


Celeritek's Wafer Qualification Procedure for these devices consists of DC, RF and reliability testing of both individual die and generic 6 to 18 GHz amplifier modules.

Celeritek's broadband power chips make up a family of GaAs FET devices which have high broadband gain and provide up to 1 watt in balanced 6 to 18 GHz amplifier circuits. These devices are also suitable for high power oscillators. In narrow band applications they offer superior associated gain.

These devices are available in chip form and are suitable for airborne, shipboard and ground-based equipment. Screening includes MIL-STD-750 Class B, Class S and commercial screening. These devices are also available in packaged form. Please consult the Packaged Power GaAs FET data sheets or contact the factory for further information.

CELERITEK

[171]



Broadband Power GaAs MESFET Chips

Mimix
BROADBAND™

August 2006 - Rev 03-Aug-06

CF010 Series

Broadband Power GaAs Chips

Specifications (T _A = 25°C)				CF003-01			CF005-01			CF010-01		
Active Layer				Ion Implanted			Ion Implanted			Ion Implanted		
Symbol	Parameters and Conditions	Frequency (GHz)	Units	Min	Typ	Max	Min	Typ	Max	Min	Typ	Max
G _L	Linear Power Gain V _{DS} = 6.0 V, I _{DS} = 80 mA V _{DS} = 6.0 V, I _{DS} = 160 mA V _{DS} = 6.0 V, I _{DS} = 300 mA	12.0	dB	8.0	9.0		7.5	8.5		7.0	8.0	
P _{1dB}	Power Output @ 1 dB GC V _{DS} = 6.0 V, I _{DS} = 80 mA V _{DS} = 6.0 V, I _{DS} = 160 mA V _{DS} = 6.0 V, I _{DS} = 300 mA	12.0	dBm	21.5	22.0		24.0	25.0		27.0	28.0	
g _m	Transconductance V _{DS} = 3.0 V, V _{GS} = 0 V		mS		120			240			480	
I _{DSS}	Drain Current V _{DS} = 3.0 V, V _{GS} = 0 V		mA	120	180	240	220	350	440	440	700	880
V _p	Pinchoff Voltage V _{DS} = 3.0 V, I _{DS} = 1 mA		Volts	-0.7	-1.3	-2.5	-0.7	-1.3	-2.5	-0.7	-1.3	-2.5
BV _{GD}	Breakdown Voltage, Gate-Drain I _{GD} = 100 μA I _{GD} = 200 μA I _{GD} = 400 μA		Volts	-5.5	-8.0		-5.5	-8.0		-5.5	-8.0	
R _{th}	Thermal Resistance		°C/W		80			50			25	


Absolute Maximum Ratings

Parameter	Symbol	Ratings
Drain-Source Voltage	V _{DS}	8V
Gate-Source Voltage	V _{GS}	-5V
Drain Current	I _{DS}	I _{DSS}
Continuous Dissipation		
CF003-01	P _T	1.6 W
CF005-01	P _T	3.0 W
CF010-01	P _T	6.0 W
Channel Temperature	T _{CH}	175°C
Storage Temperature	T _{STG}	-65°C to +175°C

Die Attach and Bonding Procedures

Die Attach: Eutectic die attach is recommended. For eutectic die attach: Preform: AuSn (80% Au, 20% Sn); Stage Temperature: 290°C, ±5°C; Handling Tool: Tweezers; Time: 1 min or less.

Wire Bonding: Wire Size: 0.7 to 1.0 mil in diameter (pre-stressed); Thermocompression bonding is preferred over thermosonic bonding. For thermocompression bonding: Stage Temperature: 250°C; Bond Tip Temperature: 150°C; Bonding Tip Pressure: 18 to 40 gms depending on size of wire.



CELERITEK

Mimix Broadband, Inc., 10795 Rockley Rd., Houston, Texas 77099
Tel: 281.988.4600 Fax: 281.988.4615 mimixbroadband.com

Page 2 of 4

Characteristic Data and Specifications are subject to change without notice. ©2006 Mimix Broadband, Inc.
Export of this item may require appropriate export licensing from the U.S. Government. In purchasing these parts, U.S. Domestic customers accept their obligation to be compliant with U.S. Export Laws.

Broadband Power GaAs MESFET Chips







Mimix
BROADBAND™

August 2006 - Rev 03-Aug-06


CF010 Series

Broadband Power GaAs Chips

Typical Performance ($T_A = 25^\circ\text{C}$)



Output Power Match Models



CELERITEK

[173]

Mimix Broadband, Inc., 10795 Rockley Rd., Houston, Texas 77099
Tel: 281.988.4600 Fax: 281.988.4615 mimixbroadband.com

Page 3 of 4

Characteristic Data and Specifications are subject to change without notice. ©2006 Mimix Broadband, Inc.
Export of this item may require appropriate export licensing from the U.S. Government. In purchasing these parts, U.S. Domestic customers accept their obligation to be compliant with U.S. Export Laws.

Broadband Power GaAs MESFET Chips

Mimix
BROADBAND™

August 2006 - Rev 03-Aug-06

CF010 Series

Broadband Power GaAs Chips

Typical Scattering Parameters, Common Source (S-Parameters Include Bonding Wire Parasitics)

CF003-01 at Power Bias

$V_{DS} = 6\text{ V}$, $I_{DS} = 80\text{ mA}$

Frequency (GHz)	S_{11}		S_{21}			S_{12}		S_{22}		K	MSG
	(Mag)	(Ang)	(dB)	(Mag)	(Ang)	(dB)	(Mag)	(Ang)	(Mag)	(Ang)	(dB)
2.0	0.91	-62	16.7	6.86	138	-28.6	0.04	59	0.23	-37	0.38
4.0	0.83	-108	14.1	5.10	107	-25.1	0.06	41	0.18	-74	0.53
6.0	0.80	-132	11.8	3.88	88	-24.0	0.06	33	0.17	-90	0.71
8.0	0.79	-155	9.6	3.01	71	-23.7	0.07	26	0.19	-120	0.88
10.0	0.78	-172	7.6	2.39	57	-24.1	0.06	24	0.23	-134	1.15
12.0	0.80	177	6.2	2.03	45	-23.3	0.07	21	0.27	-147	1.10
14.0	0.80	166	5.0	1.78	33	-23.2	0.07	17	0.31	-156	1.20
16.0	0.79	150	4.1	1.61	20	-22.1	0.08	14	0.33	-163	1.20
18.0	0.80	135	3.5	1.49	5	-21.3	0.09	9	0.32	-179	1.18

CF005-01 at Power Bias

$V_{DS} = 6\text{ V}$, $I_{DS} = 160\text{ mA}$

Frequency (GHz)	S_{11}		S_{21}			S_{12}		S_{22}		K	MSG
	(Mag)	(Ang)	(dB)	(Mag)	(Ang)	(dB)	(Mag)	(Ang)	(Mag)	(Ang)	(dB)
2.0	0.78	-109	16.1	6.35	121	-27.2	0.04	30	0.35	-177	0.69
4.0	0.82	-153	11.7	3.85	90	-25.4	0.05	23	0.42	-177	0.74
6.0	0.83	-174	8.5	2.67	72	-24.8	0.06	19	0.45	-172	0.88
8.0	0.84	177	6.2	2.03	59	-24.5	0.06	20	0.47	-170	1.02
10.0	0.85	171	4.2	1.62	49	-24.5	0.06	21	0.47	-167	1.20
12.0	0.86	165	2.8	1.38	39	-23.5	0.07	18	0.49	-164	1.14
14.0	0.86	160	1.7	1.22	29	-23.2	0.07	19	0.51	-162	1.16
16.0	0.86	154	0.5	1.06	20	-22.5	0.08	15	0.53	-160	1.14
18.0	0.87	143	-0.9	0.91	9	-22.7	0.07	13	0.57	-156	1.18


CF010-01 at Power Bias

$V_{DS} = 6\text{ V}$, $I_{DS} = 300\text{ mA}$

Frequency (GHz)	S_{11}		S_{21}			S_{12}		S_{22}		K	MSG
	(Mag)	(Ang)	(dB)	(Mag)	(Ang)	(dB)	(Mag)	(Ang)	(Mag)	(Ang)	(dB)
2.0	0.89	-146	14.1	5.09	100	-30.4	0.03	29	0.62	180	0.54
4.0	0.90	-173	8.4	2.64	78	-29.1	0.04	29	0.66	176	0.76
6.0	0.90	175	5.0	1.77	65	-28.2	0.04	31	0.67	174	0.94
8.0	0.91	170	2.6	1.34	56	-27.4	0.04	36	0.68	174	1.08
10.0	0.91	166	0.6	1.07	49	-27.4	0.04	40	0.67	174	1.26
12.0	0.91	163	-0.9	0.90	41	-26.0	0.05	37	0.69	174	1.15
14.0	0.92	161	-2.1	0.78	35	-25.5	0.05	41	0.70	175	1.10
16.0	0.91	158	-3.3	0.68	28	-24.9	0.06	36	0.72	175	1.05
18.0	0.92	149	-4.6	0.59	19	-24.8	0.06	33	0.74	173	1.04

Device Model

Parameters	CF003-01 $V_{DS} = 6\text{ V}$, $I_{DS} = 80\text{ mA}$	CF005-01 $V_{DS} = 6\text{ V}$, $I_{DS} = 160\text{ mA}$	CF010-01 $V_{DS} = 6\text{ V}$, $I_{DS} = 300\text{ mA}$	Units
L_g	0.21	0.19	0.15	nH
R_g	0.50	0.25	0.12	Ω
C_{gs}	0.71	1.13	2.58	pF
R_i	1.40	0.65	0.42	Ω
C_{gd}	0.053	0.120	0.210	pF
G_m	134	254	578	mS
τ	2.8	3.0	2.8	ps
C_{ds}	0.16	0.26	0.50	pF
R_{ds}	87	36	20	Ω
R_d	0.67	0.33	0.17	Ω
L_d	0.21	0.19	0.10	nH
R_s	0.53	0.33	0.26	Ω
L_s	0.040	0.030	0.018	nH



Wafer Qualification Procedure

100% DC Test
100% Visual Insp.

Sample Chip
Performance Test

Power,
S-Parameters,
IP3, Power Blast

Sample Circuit
Performance Tests
6-18 GHz Module

Power, Gain,
VSWR

Reliability
Assessment

Power Blast &
Burn-In

80% of tested samples must meet
specifications for wafer acceptance.

3236 Scott Boulevard
Santa Clara, California 95054
(408) 986-5060
Fax: (408) 986-5095

4-91

Specifications subject to change.

CELERITEK

[174]

Mimix Broadband, Inc., 10795 Rockley Rd., Houston, Texas 77099
Tel: 281.988.4600 Fax: 281.988.4615 mimixbroadband.com

Page 4 of 4

Characteristic Data and Specifications are subject to change without notice. ©2006 Mimix Broadband, Inc.
Export of this item may require appropriate export licensing from the U.S. Government. In purchasing these parts, U.S. Domestic customers accept their obligation to be compliant with U.S. Export Laws.