


PROCESS CP324
Small Signal MOSFET Transistor
N-Channel Enhancement-Mode Transistor Chip



PROCESS DETAILS

Process	EPITAXIAL PLANAR
Die Size	21.65 x 21.65 MILS
Die Thickness	9.0 MILS
Gate Bonding Pad Area	5.5 x 5.5 MILS
Source Bonding Pad Area	5.9 x 13.8 MILS
Top Side Metalization	Al - 30,000Å
Back Side Metalization	Au - 12,000Å

GEOMETRY



BACKSIDE DRAIN

R0

GROSS DIE PER 5 INCH WAFER

33,500

PRINCIPAL DEVICE TYPES

2N7002

R3 (22-March 2010)






www.centrasemi.com

www.DataSheet4U.com

www.DataSheet4U.com

PROCESS CP324

Typical Electrical Characteristics



R3 (22-March 2010)

www.centalsemi.com

www.DataSheet4U.com

www.DataSheet4U.com