



Stanyl

TE250F8 - 00001 物性指标

40% 玻纤增强，阻燃，应用在电子电器行业

物性指标	单位	ISO/IEC	DIN	牌号 TE250F8
常规性能				
密度	g/cm ³	ISO 1183	53479	1,77
熔点	°C	ISO 3146		295
热性能				
HDT-A (1.8 MPa)	°C	ISO 75-1	53461	290
峰值温度 (1min.)	°C	UL 746B		-
连续使用温度	°C	IEC 60216		163
- 5000 小时				
线性热膨胀系数	E-4/K	DIN 53752		
- // (23-55°C)				0,2
- ⊥ (23-55°C)				0,8
电气性能				
RTI 电气性能	°C,mm	UL 746B		*
绝缘系数	-	UL 1446		H
燃烧(厚度)	等级(mm)	UL 94		V-0 (0.8)
抗电弧径迹指数 (CTI)	PLC	IEC 60112		2
介电强度	kV/mm	IEC 60243-1		
- 干态 (23°C)				30
- 调湿后 (23°C/50%RH)				20
体电阻率	Ohm.cm	IEC 60093		
- 干态(23°C)				1E+15
- 调湿后 (23°C/50%RH)				1E+10
机械性能				
艾佐冲击(缺口)	kJ/m ²	ISO 180-1A		
- 干态 (23°C)				12
- 调湿后 (23°C/50%RH)				14
拉伸强度	MPa	ISO 527-1	53455	
- 干态 (23°C)				180
- 调湿后 (23°C/50%RH)				130
拉伸模量	MPa	ISO 527-1	53457	
- 干态 (23°C)				14500
- 调湿后 (23°C/50%RH)				12000
断裂伸长	%	ISO 527-1	53455	
- 干态 (23°C)				1,7
- 调湿后 (23°C/50%RH)				2,5
尺寸特性				
成型收缩	%	DSM		
- //				0,3
- ⊥				0,9
吸湿 (23°C/50%RH平衡时)	%	ISO 62		1,3

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and believed reliable, but DSM assumes no liability whatsoever in respect of the application, processing or use made of the aforementioned information or products, or any consequence thereof. The User undertakes all liability in respect of the application, processing or use of the aforementioned information or product, whose quality and other properties he shall verify, or any consequences thereof. No liability whatsoever shall attach to DSM for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the aforementioned information or products by the user.

DSM Kunststoffen BV. Trade Register Heerlen 31843